

Rhinolon™ P98E



FEATURES

- High wear resistance
- High extrusion resistance
- High tear resistance
- Low moisture absorption
- Excellent fluid resistance

PRODUCT DESCRIPTION

Code: P98E
Color: Sky Blue
Description: 98D Shore A Polyurethane

Property	Value	Unit	Value	Unit
Tensile Strength, Yield	6,525	PSI	45	MPa
Tensile Elongation, Break	420	%	420	%
Service Temperature Range	-40 to 250	°F	-40 to 120	°C
Specific Gravity	1.19	-	1.19	-
Hardness	98	Shore A	98	Shore A
Moisture Absorption	0	%	0	%
Modulus @ 100%	2,030	PSI	14	MPa

February 23, 2024

This information corresponds to our current information on this material. It is provided solely to provide guidelines for your evaluation. This information is not intended to substitute for any testing you may need to conduct to determine the suitability of our products for your particular application. Since we cannot anticipate all variations of the actual end use application conditions, we do not make any warranties or assume any liabilities in connection with any use of this information.

Product Performance. Affordability. Availability.



3702 Vanguard Dr. | Fort Wayne, IN 46819 | USA
Telephone: 260-615-3951 | Fax: 260-436-5267
info@BlackHawkSeals.com